

ZYREX APPLICATION GUIDE

CONCRETE APPLICATION

WEATHERED, AGED OR PREVIOUSLY SEALED

- 1) Repair any cracks and surfaces imperfections in concrete
- 2) Clean off all oil and dirt using a mixture of one (1) part Muriatic Acid and three (3) parts water. Scrub all dirty areas and oil patches with stiff brush.
- 3) Power wash to remove all oil and Muriatic Acid from concrete.
- 4) Grind floor with floor sander using 16 to 24 grit sandpaper.
- 5) Mix equal amounts of Part A, Part B and Acetone on first coat only!
Ex: 1Gal A, 1Gal B, & 1Gal Acetone
- 6) Apply first coat very thin. This coat is to etch into concrete.
- 7) For coats 2 and 3 mix equal parts of A & B

NEW CONCRETE, NO SEALER

- 1) Power wash to remove all dust and debris
- 2) Mix equal amounts of Part A, Part B and Acetone on first coat only!
Ex: 1Gal A, 1Gal B, & 1Gal Acetone
- 3) Apply first coat very thin. This coat is to etch into concrete.
- 4) For coats 2 and 3 mix equal parts of A & B